

## **Product Information Bulletin**

	•
BULLETIN NO.	212
ISSUED:	March 27, 2014
REPLACES:	June 1, 2011

## PlastiSpan® HD Insulation Material Property Data Sheet CAN/ULC-S701-11, Type 2

CAN/ULC-S701-11, **Standard for Thermal Insulation, Polystyrene, Boards and Pipe Covering** is the National Standard of Canada for moulded expanded polystyrene (EPS) insulation. The table below provides material properties for **PlastiSpan HD** insulation meeting CAN/ULC-S701, Type 2.

Material Property	Test Method	Units	Values <sup>1</sup>
Thermal Resistance Minimum RSI per 25 mm (R per inch)	ASTM C518	m²₌°C/W	0.70
		(ft²•h•°F/BTU)	(4.04)
Compressive Resistance Minimum @ 10% Deformation	ASTM D1621	kPa	110
		(psi)	(16)
Flexural Strength Minimum	ASTM C203	kPa	240
		(psi)	(35)
Water Vapour Permeance <sup>2</sup> Maximum	ASTM E96	ng/(Pa·s·m²)	200
		(Perms)	(3.5)
Water Absorption <sup>3</sup> Maximum	ASTM D2842	% By volume	4.0
Dimensional Stability  Maximum, 7 Days @ $70 \pm 2 \degree C$ (158 $\pm 4 \degree F$ )	ASTM D2126	% Linear Change	1.5
Limiting Oxygen Index Minimum	ASTM D2863	%	24

<sup>1.</sup> PlastiSpan HD insulation properties are third party certified under a certification program administered by Intertek Testing Services and listed by the Canadian Construction Materials Centre (CCMC) under evaluation listing number 12425-L (Type 2).

<sup>2.</sup> WVP values quoted are maximum values for 25-mm (1-inch) thick samples with natural skins intact. Lower values will result for thicker materials.

<sup>3.</sup> The water absorption laboratory test method involves complete submersion under a head of water for 96 hours. The water absorption value above is applicable to specific end-use design requirements only to the extent that the end-use conditions are similar to test method requirements.