

Nordic Void is a strong, flexible and water resistant closed-cell elastomeric Void Form designed to be compliant yet resilient when used under suitable pile/pile-cap (caisson), pile cap/grade beam and slab on grade foundations.

MATERIAL PROPERTY	MATERIAL DATA	TESTING METHOD
Thermal Conductivity k (mean) @ 24 °C (75 °F)	0.062 W/m*K (.43 Btu-in/hr-ft ² -F)	ASTM C518
Thermal Resistance R-Value (RSI) @ 24 °C (75 °F)	R – 2.3 Hr-ft ² -°F/Btu (RSI – 0.41 m ² ·K/W)	ASTM C518
Compressive Deflection: 10% Compression 20% Compression 25% Compression 30% Compression 40% Compression 50% Compression	43.4 kPa (6.3 psi) 53.8 kPa (7.8 psi) 59.3 kPa (8.6 psi) 66.9 kPa (9.7 psi) 86.9 kPa (12.6 psi) 116.5 kPa (16.9 psi)	ASTM D1621
Multiple Cycle Rebound @ 0°C (32°F) Rebound following multiple cycles of 25% compression performed @ 0°C following a 24 hour pre-load at 24.1 kPa (3.5 psi). Value reported is the per-cent recovered of the pre-load thickness.	> 93% (% recovery)	Norseman MPS-112
Compression Set: @ 50% compression	< 20%	ASTM D3575
Compressive Creep 300 hours & 1,000 hours @ 17.3 kPa (2.5 psi) 300 hours & 1,000 hours @ 24.1 kPa (3.5 psi)	< 5% @ 300 h / <8% @ 1,000 h <7% @ 300 h / <15% @ 1,000 h	ASTM D3575
Tensile Strength at Peak	214 kPa (31 psi)	ASTM D3575
Tear Strength	1.75 kN/m (10 lb/in.)	ASTM D3575
Thermal Stability - % shrinkage	< 2.0 %	ASTM D3575
Water Absorption	1.5 kg/m ² (0.3 lb/ft ²)	ASTM D3575

IMPORTANT: Norseman Inc presents the information and data in this document in good faith based on manufacturer's documentation and/or third party independent testing and believes them to be correct as of the time of publication. While values shown are typical of these products they should not be construed as specification limits. NORSEMAN MAKES NO WARRANTIES, EITHER EXPRESSED OR IMPLIED, INCLUDING THE WARRANTY OF MERCHANTABILITY OF OR FITNESS FOR A PARTICULAR PURPOSE, WITH RESPECT TO THE INFORMATION AND DATA IN THIS PUBLICATION OR AS TO ANY PRODUCT. NORSEMAN ACCEPTS NO CONTRACTUAL LIABILITY OF ANY KIND TO ANY PERSON IN RESPECT OF ITS CONTENTS OR ANY USE THEREOF, NOR MUST IT BE ASSUMED THAT ANY SUCH USE WILL NOT INFRINGE ANY PATENT. Users should test each application to determine suitability of the product for the intended use.

Updated: 08/07/2014
Supersedes: 06/07/2011